

**EVEREST FOLDING CARTON BOARD DATA SHEET**

**Grade:** 1255

**Description:** EVEREST FCB 22PT

**Nominal Basis Weight:** 235 Lbs./3,000 Sq. Ft.  
 382 GSM

Description		Target Values	
<b>Basis Weight, T411</b>			
		Lbs. /3000 Sq. Ft.	241.2
		GSM	392.5
<b>Caliper, T410</b>			
		.001 inch	22.0
		mm	0.559
<b>Stiffness, Taber V-5</b>			
	mNm - MD	38.26	g-cm - MD
			390.0
	mNm - CD	19.33	g-cm - CD
			197.0
<b>Brightness, % T452</b>			
		CS	87.5
		UCS	83.5
<b>Moisture, % T412</b>			
			5.8
<b>Gloss, % (75 degree) T480</b>			
			55.0
<b>Smoothness, Sheffield Units T538</b>			
		CS	38.0
		UCS	243.0
<b>Shade, b * CIELab D65 @ 10 degrees</b>			
			0.5

Values are grade targets for uncoated "as made" board unless specified otherwise. Values are subject to revision without notice.