

English **CreatorSilk**
2 Side Coated Silk

Property		Units	Tolerance														
Substance	ISO 536	gsm	± 4%	90	100	115	125	130	135	150	170	200	225	250	270	300	350
Thickness	ISO 534	µm	± 7%	78	86	93	105	109	113	129	134	166	196	225	243	278	340
Whiteness CIE																	
D65 /10° (Outdoor)	ISO 11475	Index	-3	118	118	118	118	118	118	118	118	118	118	118	118	118	118
C/2° (Indoor)	ISO 11476	Index	-3	102	102	102	102	102	102	102	102	102	102	102	102	102	102
Opacity	ISO 2471	%	-2	91,0	92,0	92,5	93,5	94,0	96,0	96,5	97,5	98,3	98,9	99,1	99,3	99,5	99,6
Relative Humidity	TAPPI T-502	%	± 7	48	48	48	48	48	48	48	48	48	48	44	44	44	44
Smoothness Bekk	ISO 5627	s	-100	300	300	300	300	300	250	250	300	300	250	210	200	160	70

- Last updated: **19/08/2009**
- Values are subject to change without notice.

Español **CreatorSilk**
Estucado 2 Caras Semimate

Propiedad		Unidades	Tolerancia														
Gramaje	ISO 536	g/m²	± 4%	90	100	115	125	130	135	150	170	200	225	250	270	300	350
Calibre	ISO 534	µm	± 7%	78	86	93	105	109	113	129	134	166	196	225	243	278	340
Blancura CIE																	
D65 /10° (Exterior)	ISO 11475	Índice	-3	118	118	118	118	118	118	118	118	118	118	118	118	118	118
C/2° (Interior)	ISO 11476	Índice	-3	102	102	102	102	102	102	102	102	102	102	102	102	102	102
Opacidad	ISO 2471	%	-2	91,0	92,0	92,5	93,5	94,0	96,0	96,5	97,5	98,3	98,9	99,1	99,3	99,5	99,6
Humedad relativa	TAPPI T-502	%	± 7	48	48	48	48	48	48	48	48	48	48	44	44	44	44
Lisura Bekk	ISO 5627	s	-100	300	300	300	300	300	250	250	300	300	250	210	200	160	70

- Última actualización: **19/08/2009**
- Los valores están sujetos a cambio sin aviso previo.

Français **CreatorSilk**
Couché 2 Faces Demi-mat

Propriété		Unités	Tolérance														
Grammage	ISO 536	g/m²	± 4%	90	100	115	125	130	135	150	170	200	225	250	270	300	350
Épaisseur	ISO 534	µm	± 7%	78	86	93	105	109	113	129	134	166	196	225	243	278	340
Blancheur CIE																	
D65 /10° (Extérieur)	ISO 11475	Indice	-3	118	118	118	118	118	118	118	118	118	118	118	118	118	118
C/2° (Intérieur)	ISO 11476	Indice	-3	102	102	102	102	102	102	102	102	102	102	102	102	102	102
Opacité	ISO 2471	%	-2	91,0	92,0	92,5	93,5	94,0	96,0	96,5	97,5	98,3	98,9	99,1	99,3	99,5	99,6
Humidité relative	TAPPI T-502	%	± 7	48	48	48	48	48	48	48	48	48	48	44	44	44	44
Lissé Bekk	ISO 5627	s	-100	300	300	300	300	300	250	250	300	300	250	210	200	160	70

- Dernière actualisation: **19/08/2009**
- Les valeurs sont susceptibles d'être modifiées sans préavis.

Português **CreatorSilk**
Couché 2 Faces Semi-mate

Propriedade		Unidade	Tolerância														
Gramagem	ISO 536	gsm	± 4%	90	100	115	125	130	135	150	170	200	225	250	270	300	350
Calibre	ISO 534	µm	± 7%	78	86	93	105	109	113	129	134	166	196	225	243	278	340
Brancura CIE																	
D65 /10° (Outdoor)	ISO 11475	Índice	-3	118	118	118	118	118	118	118	118	118	118	118	118	118	118
C/2° (Indoor)	ISO 11476	Índice	-3	102	102	102	102	102	102	102	102	102	102	102	102	102	102
Opacidade	ISO 2471	%	-2	91,0	92,0	92,5	93,5	94,0	96,0	96,5	97,5	98,3	98,9	99,1	99,3	99,5	99,6
Humidade relativa	TAPPI T-502	%	± 7	48	48	48	48	48	48	48	48	48	48	44	44	44	44
Lisura Bekk	ISO 5627	s	-100	300	300	300	300	300	250	250	300	300	250	210	200	160	70

- Última actualização: **19/08/2009**
- Os valores estão sujeitos a mudanças sem pré-aviso.