

English **CreatorStar**

2 Side Coated Gloss

Property		Units	Tolerance														
Substance	ISO 536	gsm	± 4%	90	100	115	125	130	135	150	170	200	225	250	270	300	350
Thickness	ISO 534	µm	± 7%	70	78	85	93	96	100	110	122	140	163	190	206	230	293
Whiteness CIE																	
D65 /10° (Outdoor)	ISO 11475	Index	-3	123	123	123	123	123	123	123	123	123	123	123	123	123	123
C/2° (Indoor)	ISO 11476	Index	-3	105	105	105	105	105	105	105	105	105	105	105	105	105	105
Opacity	ISO 2471	%	-2	90,0	91,0	93,5	93,7	94,0	94,5	96,0	97,0	97,5	98,0	98,5	98,5	99,0	99,5
Paper Gloss	TAPPI T-480	%	± 5	66	67	76	77	77	77	77	76	76	76	76	76	76	76
Relative Humidity	TAPPI T-502	%	± 7	48	48	48	48	48	48	48	48	48	48	44	44	44	44

- Last updated: **19/08/2009**
- Values are subject to change without notice.

Español **CreatorStar**

Estucado 2 Caras Brillante

Propiedad		Unidades	Tolerancia														
Gramaje	ISO 536	g/m²	± 4%	90	100	115	125	130	135	150	170	200	225	250	270	300	350
Calibre	ISO 534	µm	± 7%	70	78	85	93	96	100	110	122	140	163	190	206	230	293
Blancura CIE																	
D65 /10° (Exterior)	ISO 11475	Índice	-3	123	123	123	123	123	123	123	123	123	123	123	123	123	123
C/2° (Interior)	ISO 11476	Índice	-3	105	105	105	105	105	105	105	105	105	105	105	105	105	105
Opacidad	ISO 2471	%	-2	90,0	91,0	93,5	93,7	94,0	94,5	96,0	97,0	97,5	98,0	98,5	98,5	99,0	99,5
Brillo de papel	TAPPI T-480	%	± 5	66	67	76	77	77	77	77	76	76	76	76	76	76	76
Humedad relativa	TAPPI T-502	%	± 7	48	48	48	48	48	48	48	48	48	48	44	44	44	44

- Última actualización: **19/08/2009**
- Los valores están sujetos a cambio sin aviso previo.

Français **CreatorStar**

Couché 2 Faces Brillant

Propriété		Unités	Tolérance														
Grammage	ISO 536	g/m²	± 4%	90	100	115	125	130	135	150	170	200	225	250	270	300	350
Épaisseur	ISO 534	µm	± 7%	70	78	85	93	96	100	110	122	140	163	190	206	230	293
Blancheur CIE																	
D65 /10° (Extérieur)	ISO 11475	Indice	-3	123	123	123	123	123	123	123	123	123	123	123	123	123	123
C/2° (Intérieur)	ISO 11476	Indice	-3	105	105	105	105	105	105	105	105	105	105	105	105	105	105
Opacité	ISO 2471	%	-2	90,0	91,0	93,5	93,7	94,0	94,5	96,0	97,0	97,5	98,0	98,5	98,5	99,0	99,5
Brillance du papier	TAPPI T-480	%	± 5	66	67	76	77	77	77	77	76	76	76	76	76	76	76
Humidité relative	TAPPI T-502	%	± 7	48	48	48	48	48	48	48	48	48	48	44	44	44	44

- Dernière actualisation: **19/08/2009**
- Les valeurs sont susceptibles d'être modifiées sans préavis.

Português **CreatorStar**

Couché 2 Faces Brilhante

Propriedade		Unidade	Tolerância														
Gramagem	ISO 536	gsm	± 4%	90	100	115	125	130	135	150	170	200	225	250	270	300	350
Calibre	ISO 534	µm	± 7%	70	78	85	93	96	100	110	122	140	163	190	206	230	293
Brancura CIE																	
D65 /10° (Outdoor)	ISO 11475	Índice	-3	123	123	123	123	123	123	123	123	123	123	123	123	123	123
C/2° (Indoor)	ISO 11476	Índice	-3	105	105	105	105	105	105	105	105	105	105	105	105	105	105
Opacidade	ISO 2471	%	-2	90,0	91,0	93,5	93,7	94,0	94,5	96,0	97,0	97,5	98,0	98,5	98,5	99,0	99,5
Brilho do papel	TAPPI T-480	%	± 5	66	67	76	77	77	77	77	76	76	76	76	76	76	76
Humidade relativa	TAPPI T-502	%	± 7	48	48	48	48	48	48	48	48	48	48	44	44	44	44

- Última actualização: **19/08/2009**
- Os valores estão sujeitos a mudanças sem pré-aviso.