

sappi**DATASHEET QUATRO GLOSS****quatro**

| PARAMETER | STANDARD | UNIT | | | | | | | | | | | | | | | | | TOLERANCES |
|--------------------------------|-----------|--------------------|------|------|------|------|------|------|------|------|------|--|--|--|--|--|--|--|------------|
| STANDARD QUALITY VALUES | | | | | | | | | | | | | | | | | | | |
| BASIS WEIGHT | ISO 536 | g/m ² | 90 | 100 | 115 | 130 | 150 | 170 | 200 | 250 | 300 | | | | | | | | ± 4 % |
| BRIGHTNESS (Illuminant D65/0°) | ISO 2470 | % | 95 | 95 | 95 | 95 | 95 | 95 | 95 | 95 | 95 | | | | | | | | ± 2 |
| GLOSS DIN 75° (MD) | DIN 54502 | % | 45 | 46 | 47 | 47 | 47 | 47 | 47 | 47 | 47 | | | | | | | | ± 5 |
| OPACITY | ISO 2471 | % | 90 | 92 | 93 | 94 | 95,5 | 96,5 | 97,5 | 98,5 | 99 | | | | | | | | ± 2 |
| RELATIVE HUMIDITY (23°C) | TAPPI 502 | % | 50 | 50 | 50 | 50 | 50 | 50 | 50 | 50 | 50 | | | | | | | | ± 5 |
| PH VALUE | ISO 6588 | - | >7 | >7 | >7 | >7 | >7 | >7 | >7 | >7 | >7 | | | | | | | | - |
| SPEC. VOLUME | ISO 534 | cm ³ /g | 0,73 | 0,73 | 0,73 | 0,73 | 0,73 | 0,75 | 0,75 | 0,72 | 0,74 | | | | | | | | ± 6 % |

VALID FROM 11-AUG-2009

Printouts are uncontrolled copies.

Refer to the intranet/internet for the actual version.